

## TECHNICAL DATA SHEET

### CELATOM<sup>®</sup> MW-25

#### PHYSICAL AND CHEMICAL PROPERTIES

Structure .....	Flux-Calcined
Color .....	White
Brightness (Y) .....	90
Sieve Analysis (Tyler)	
% + 150 Mesh (> 105 microns) .....	---
% + 325 Mesh (> 44 microns) .....	0.1
Median Particle Diameter (microns) .....	12.6
Hegman .....	3.5
pH (10% slurry) .....	10.0
Free Moisture (Maximum % H <sub>2</sub> O) .....	0.5
(Typical % H <sub>2</sub> O) .....	0.2
Density:	(lb/ft <sup>3</sup> ) (g/l)
Wet Bulk .....	25 400
Dry Bulk .....	13 210
Oil Absorption (Gardner Coleman) lbs/100lbs .....	120
Specific Gravity .....	2.33
Refractive Index .....	1.46

#### CHEMICAL ANALYSIS

SiO <sub>2</sub> .....	89.5%
Al <sub>2</sub> O <sub>3</sub> .....	4.1%
Fe <sub>2</sub> O <sub>3</sub> .....	1.5%
CaO .....	0.6%
MgO .....	0.3%
Other Oxides .....	4.0%
Loss on Ignition .....	Nil

Updated: 01/2013

**UNCONTROLLED COPY FOR INFORMATION PURPOSES ONLY.**  
All information shown is typical – **NOT TO BE USED FOR SPECIFICATIONS.**  
Read appropriate Material Safety Data Sheet before using.  
Contact EP Minerals for product specification approval.